



Available as  
**PEFC**  
certified paper on  
request

### Technical data

Basis weight [g/m <sup>2</sup> ] ISO 536	57	60	70
Brightness D65/10° [%] ISO 2470	83	83	83
Colour D65/10° [%]			
L*	91	91	91
a*	-0.20	-0.20	-0.20
b*	-1.5	-1.5	-1.5
Opacity [%] ISO 2471	90	91	93
Gloss Hunter 75° [%] <sup>②</sup> ISO 8245/1	46	46	46
Gloss Lehmann 75° [%] ISO 8254/1	42	42	42
Roughness PPS 10 [µm] ISO 8791-4	0.90	0.90	0.90
Bulk [cm <sup>3</sup> /g] <sup>③</sup>	0.8	0.8	0.8

② The process control is based on Lehmann gloss – the Hunter gloss specification serves as a reference value only

Subject to change. 10/2008

③ No guaranteed value – subject to production variations

Please check for availability as all basis weights may be subject to production requirements.

#### Product description:

MY SILK *gravure* is a wood-containing lightweight roto-  
gravure paper with an attractive silk finish.

#### Examples of use:

Magazines, exclusive catalogues, high quality supplements  
and high circulation brochures

#### Composition:

Coating weight: 33 % approx.  
Base paper composition  
(depending on basis weight):  
40–45 % mechanical pulp  
40–45 % chemical pulp  
10–20 % DIP

#### Reel specification:

– Minimum width: 50 cm  
– Maximum width: 450 cm  
– Diameter: max. 135 cm  
– Core diameter: 76 mm or 150 mm