



Available as
PEFC
certified paper on
request

Technical data

	50 [♦]	60	65	70	80	90	100 [♦]	115 [♦]
Basis weight [g/m ²] ISO 536	50 [♦]	60	65	70	80	90	100 [♦]	115 [♦]
Brightness D65/10° [%] ISO 2470	89	91	91	91	91	91	92	92
Colour D65/10° [%] L*	93.2	93.5	93.5	93.5	93.8	93.8	93.8	93.8
a*	0.2	0.5	0.5	0.5	0.7	0.7	0.7	0.7
b*	-3.0	-3.4	-3.4	-3.4	-4.0	-4.0	-4.0	-4.0
Opacity [%] ISO 2471	86	89	90	90	94	95	97	97.5
Gloss Hunter 75° [%] [Ⓢ] ISO 8245/1	16	22	22	24	28	29	29	29
Gloss Lehmann 75° [%] ISO 8254/1	13	19	19	21	25	26	26	26
Roughness PPS 10 [µm] [Ⓢ] ISO 8791-4	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
Bulk [cm ³ /g] [Ⓢ]	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0

♦ On request

Ⓢ The process control is based on Lehmann gloss – the Hunter gloss specification serves as a reference value only

Ⓢ No guaranteed value – subject to production variations

Subject to change. 02/2008

Product description:

MY REX *silk* is a high bright wood containing silk coated sheet fed paper with excellent readability and a warm shade.

Composition:

Coating weight: 33 % approx.

Base paper composition

(depending on basis weight):

35–45 % chemical pulp

65–55 % mechanical pulp

Examples of use:

High quality brochures, magazines, books

Sheet specification:

All standard sizes

Other sizes on request

Maximum sheet size: 120 x 162 cm

Prepress information:

Prepress profile for paper type 3

according ISO 12647-2 recommended