



Available as
PEFC or FSC
certified paper on
request

Technical data

	60 [♦]	65 [♦]	70	75	80	85 [♦]	90	100	115	135
Basis weight [g/m ²] ISO 536										
Brightness D65/10° [%] ISO 2470	90	90	90	90	91	91	91	91	91	91
Colour D65/10° [%] L*	92.5	92.5	92.5	92.5	92.5	92.5	92.5	92.5	92.5	92.5
a*	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
b*	-5.5	-5.5	-5.5	-5.5	-5.5	-5.5	-5.5	-5.5	-5.5	-5.5
Opacity [%] ISO 2471	92	93	94	95	96	96	97	97	98	99
Gloss Hunter 75° [%] [Ⓢ] ISO 8245/1	59	61	63	65	65	66	66	67	69	69
Gloss Lehmann 75° [%] [Ⓢ] ISO 8254/1	59	60	61	63	63	64	65	67	69	69
Roughness PPS 10 [µm] [Ⓢ] ISO 8791-4	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
Bulk [cm ³ /g] [Ⓢ]	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8

♦ On request

Ⓢ The process control is based on Lehmann gloss (MD Albruck) and Hunter gloss (Myllykoski Paper)

Ⓢ No guaranteed value – subject to production variations

Subject to change. 07/2009

Product description:

MY BRITE is a high bright wood containing light weight coated (LWC) and medium weight coated (MWC) gloss paper for HSWO with a modern blue-white shade.

Composition:

Coating weight: 33 % approx.

Base paper composition

(depending on basis weight):

35–45 % chemical pulp

65–55 % mechanical pulp

Examples of use:

High quality supplements, brochures, magazines, catalogues

Reel specification:

Mylykoski Paper (60-90 g/m²):

– Minimum width: 40 cm (packed in pairs)

– Maximum width: 268 cm

– Diameter: max. 130 cm

– Core diameter: 76 mm or 150 mm

MD Albruck (65-135 g/m²):

– Minimum width: 30 cm (packed in pairs)

– Maximum width: 250 cm

– Diameter: max. 125 cm

– Core diameter: 76 mm or 150 mm

Prepress information:

Prepress profile for paper type 1

according ISO 12647-2 recommended



Available as
PEFC
certified paper on
request

Technical data					
	60	65	70	80	90
Basis weight [g/m²] ISO 536	60	65	70	80	90
Brightness D65/10° [%] ISO 2470	89	89	89	90	90
Colour D65/10° [%] L*	92	92	92	92	92
a*	0.6	0.6	0.6	0.6	0.6
b*	-5.5	-5.5	-5.5	-5.5	-5.5
Opacity [%] ISO 2471	91	93	93	94	96
Gloss Hunter 75° [%] [Ⓢ] ISO 8245/1	61	61	62	64	64
Gloss Lehmann 75° [%] ISO 8254/1	58	58	60	62	62
Roughness PPS 10 [µm] [Ⓢ] ISO 8791-4	1.1	1.1	1.1	1.1	1.1
Bulk [cm ³ /g] [Ⓢ]	0.8	0.8	0.8	0.8	0.8

[Ⓢ] The process control is based on Lehmann gloss – the Hunter gloss specification serves as a reference value only.

Subject to change. 03/2009

[Ⓢ] No guaranteed value – subject to production variations.

Product description:

MY BRITE is a high bright wood containing light weight coated (LWC) and medium weight coated (MWC) gloss paper for HSWO with a modern blue-white shade.

Composition:

Coating weight: 33 % approx.
Base paper composition
(depending on basis weight):
30 % chemical pulp
54% mechanical pulp
16 % DIP

Examples of use:

High quality supplements, brochures, magazines, catalogues

Reel specification:

- Minimum width: 40 cm (packed in pairs)
- Maximum width: 370 cm
- Diameter: max. 125 cm
- Core diameter: 76 mm or 150 mm

Prepress information:

Prepress profile for paper type 1
according ISO 12647-2 recommended