



Available as  
**PEFC**  
certified paper on  
request

### Technical data

	50 <sup>♦</sup>	60	65	70	80	90
Basis weight [g/m <sup>2</sup> ] ISO 536						
Brightness D65/10° [%] ISO 2470	80	82	82	82	83	83
Colour D65/10° [%] L*	91.5	92.2	92.2	92.2	92.2	92.2
a*	-1	-0.2	-0.2	-0.2	-0.1	-0.1
b*	0	-1.5	-1.5	-1.5	-1.5	-1.5
Opacity [%] ISO 2471	87	90	91	92	95	96
Gloss Hunter 75° [%] <sup>Ⓜ</sup> ISO 8245/1	16	22	22	24	28	29
Gloss Lehmann 75° [%] ISO 8254/1	13	19	19	21	25	26
Roughness PPS 10 [µm] <sup>Ⓝ</sup> ISO 8791-4	2.5	2.5	2.5	2.5	2.5	2.5
Bulk [cm <sup>3</sup> /g] <sup>Ⓝ</sup>	1.0	1.0	1.0	1.0	1.0	1.0

♦ On request

Ⓜ The process control is based on Lehmann gloss – the Hunter gloss specification serves as a reference value only

Ⓝ No guaranteed value – subject to production variations

Subject to change. 02/2008

#### Product description:

MY NOVA *silk* is a wood containing coated sheet fed paper with excellent readability due to the low reflecting silk surface.

#### Composition:

Coating weight: 33 % approx.

Base paper composition

(depending on basis weight):

35–45 % chemical pulp

65–55 % mechanical pulp

#### Examples of use:

Brochures, magazines, books

#### Sheet specification:

All standard sizes

Other sizes on request

Maximum sheet size: 120 x 162 cm

#### Prepress information:

Prepress profile for paper type 3

according ISO 12647-2 recommended