

**Technical data**

Basis weight [g/m <sup>2</sup> ] ISO 536	60	65	70	80	90	100 <sup>♦</sup>	115 <sup>♦</sup>
Brightness D65/10° [%] ISO 2470	83	83	83	84	84	84	84
Colour D65/10° [%] L*	91.5	91.5	91	91.2	91.2	91.5	91.5
a*	0.1	0.1	0.1	0.4	0.4	0.6	0.6
b*	-4.0	-4.0	-4.0	-4.0	-4.0	-4.0	-4.0
Opacity [%] ISO 2471	88	90	91	94	95	96	97
Gloss Hunter 75° [%] <sup>Ⓢ</sup> ISO 8245/1	54	57	62	65	67	69	69
Gloss Lehmann 75° [%] ISO 8254/1	52	55	60	63	65	67	67
Roughness PPS 10 [µm] <sup>Ⓢ</sup> ISO 8791-4	1.1	1.1	1.1	1.1	1.1	1.1	1.1
Bulk [cm <sup>3</sup> /g] <sup>Ⓢ</sup>	0.8	0.8	0.8	0.8	0.8	0.8	0.8

<sup>♦</sup> On request

<sup>Ⓢ</sup> The process control is based on Lehmann gloss – the Hunter gloss specification serves as a reference value only

<sup>Ⓢ</sup> No guaranteed value – subject to production variations

Subject to change. 02/2008

**Product description:**

MY NOVA *gloss* is a wood-containing sheet fed paper with excellent print gloss.

**Composition:**

Coating weight: 33 % approx.

Base paper composition

(depending on basis weight):

35–45 % chemical pulp

65–55 % mechanical pulp

**Examples of use:**

Brochures, magazines, books

**Sheet specification:**

All standard sizes

Other sizes on request

Maximum sheet size: 120 x 162 cm

**Prepress information:**

Prepress profile for paper type 3

according ISO 12647-2 recommended