



Available as
PEFC
 certified paper on
 request

Technical data

| | 60 | 70 | 75 | 80 | 90 | 100 | 115 | 135 |
|--|------|------|------|------|------|------|------|------|
| Basis weight [g/m ²] ISO 536 | 60 | 70 | 75 | 80 | 90 | 100 | 115 | 135 |
| Brightness D65/10° [%] ISO 2470 | 92 | 93 | 93 | 94 | 94 | 94 | 94 | 94 |
| Colour D65/10° [%] L* | 93.5 | 93.5 | 93.5 | 93.5 | 93.5 | 93.5 | 93.5 | 93.5 |
| a* | 0.5 | 0.6 | 0.6 | 0.7 | 0.7 | 0.7 | 0.7 | 0.7 |
| b* | -5.7 | -5.8 | -5.8 | -6.0 | -6.0 | -6.0 | -6.0 | -6.0 |
| Opacity [%] ISO 2471 | 89 | 92 | 93 | 94 | 95 | 97 | 97 | 98 |
| Gloss Hunter 75° [%] [Ⓜ] ISO 8245/1 | 19 | 19 | 19 | 19 | 20 | 21 | 21 | 21 |
| Gloss Lehmann 75° [%] ISO 8254/1 | 16 | 16 | 16 | 16 | 17 | 18 | 18 | 18 |
| Roughness PPS 10 [µm] [Ⓢ] ISO 8791-4 | 3.5 | 3.5 | 3.5 | 3.5 | 3.5 | 3.5 | 3.5 | 3.5 |
| Bulk [cm ³ /g] [Ⓢ] | 1.1 | 1.1 | 1.1 | 1.1 | 1.1 | 1.1 | 1.1 | 1.1 |

[Ⓜ] The process control is based on Lehmann gloss – the Hunter gloss specification serves as a reference value only

Subject to change. 02/2008

[Ⓢ] No guaranteed value – subject to production variations

Product description:

MY SOL *matt* is a high bright wood containing matt coated sheet fed paper with a blue-white shade and excellent readability.

Composition:

Coating weight: 33 % approx.
 Base paper composition
 (depending on basis weight):
 35–45 % chemical pulp
 65–55 % mechanical pulp

Examples of use:

Highest quality brochures, magazines, books

Sheet specification:

All standard sizes
 Other sizes on request
 Maximum sheet size: 120 x 162 cm

Prepress information:

Prepress profile for paper type 2
 according ISO 12647-2 recommended