



Available as  
**PEFC**  
 certified paper on  
 request

**Technical data**

	70	80	90	100 <sup>♦</sup>	115 <sup>♦</sup>
Basis weight [g/m <sup>2</sup> ] ISO 536	70	80	90	100 <sup>♦</sup>	115 <sup>♦</sup>
Brightness D65/10° [%] ISO 2470	89	90	90	90	90
Colour D65/10° [%] L*	92.7	92.7	92.7	92.7	92.7
a*	0.5	0.7	0.7	0.7	0.7
b*	-4.3	-4.7	-4.7	-4.7	-4.7
Opacity [%] ISO 2471	90	93	94.5	96	97
Gloss Hunter 75° [%] <sup>Ⓢ</sup> ISO 8245/1	62	65	67	69	69
Gloss Lehmann 75° [%] ISO 8254/1	60	63	65	67	67
Roughness PPS 10 [µm] <sup>Ⓢ</sup> ISO 8791-4	1.1	1.1	1.1	1.1	1.1
Bulk [cm <sup>3</sup> /g] <sup>Ⓢ</sup>	0.8	0.8	0.8	0.8	0.8

<sup>♦</sup> On request

Subject to change. 02/2008

<sup>Ⓢ</sup> The process control is based on Lehmann gloss – the Hunter gloss specification serves as a reference value only

<sup>Ⓢ</sup> No guaranteed value – subject to production variations

**Product description:**

MY REX *gloss* is a high bright wood-containing coated sheet fed paper with a warm shade.

**Composition:**

Coating weight: 33 % approx.

Base paper composition

(depending on basis weight):

35–45 % chemical pulp

65–55 % mechanical pulp

**Examples of use:**

High quality brochures, magazines, books

**Sheet specification:**

All standard sizes

Other sizes on request

Maximum sheet size: 120 x 162 cm

**Prepress information:**

Prepress profile for paper type 3

according ISO 12647-2 recommended