

Technical data

Basis weight [g/m ²] ISO 536	57	60
Brightness D65/10° [%] ISO 2470	79	79
Colour D65/10° [%] L*	92	92
a*	-0.45	-0.45
b*	0.0	0.0
Opacity [%] ISO 2471	90	91
Gloss Hunter 75° [%] [Ⓜ] ISO 8245/1	57	57
Gloss Lehmann 75° [%] ISO 8254/1	57	57
Roughness PPS 10 [µm] ISO 8791-4	0.90	0.90
Bulk [cm ³ /g] [Ⓝ]	0.8	0.8

[Ⓜ] The process control is based on Lehmann gloss – the Hunter gloss specification serves as a reference value only

Subject to change. 03/2010

[Ⓝ] No guaranteed value – subject to production variations

Please check for availability as all basis weights may be subject to production requirements.

Product description:

MY STAR *gravure* is a wood containing lightweight coated rotogravure paper.

Examples of use:

Magazines, exclusive catalogues, high quality supplements and high circulation brochures

Composition:

Coating weight: 33 % approx.
 Base paper composition
 (depending on basis weight):
 35–45 % mechanical pulp
 35–45 % chemical pulp
 10–20 % DIP

Reel specification:

– Minimum width: 50 cm
 – Maximum width: 450 cm
 – Diameter: max. 135 cm
 – Core diameter: 76 mm or 150 mm