



Available as  
**PEFC or FSC**  
certified paper on  
request

<b>Technical data</b>					
Basis weight [g/m <sup>2</sup> ] ISO 536	54	57	60	65	70
Brightness D65/10° [%] ISO 2470	80	81	81	83	83
Colour D65/10° [%]					
L*	91	92	92	93	93
a*	-0.4	-0.4	-0.4	-0.4	-0.4
b*	-0.4	-0.4	-0.4	-0.8	-0.8
Opacity [%] ISO 2471	91	92	92	93	94
Gloss Hunter 75° [%] ISO 8245/1	38	38	38	38	38
Gloss Lehmann 75° [%] <sup>Ⓢ</sup> ISO 8254/1	34	34	34	34	34
Roughness PPS 10 [µm] ISO 8791-4	1.2	1.2	1.2	1.2	1.2
Bulk [cm <sup>3</sup> /g] <sup>Ⓢ</sup>	1.0	1.0	1.0	1.0	1.0

<sup>Ⓢ</sup> The process control is based on Hunter gloss – the Lehmann gloss specification serves as a reference value only

Subject to change. 07/2009

<sup>Ⓢ</sup> No guaranteed value – subject to production variations

Please check for availability as all basis weights may be subject to production requirements.

**Product description:**

MY GOLD *silk* is the leading grade for superior HSWO print production with its optimal combination of brightness, opacity and bulk.

**Composition:**

20 % chemical pulp  
80 % mechanical pulp

**Examples of use:**

premium catalogues, magazines and top quality advertising materials

**Reel specification:**

– minimum width: 41 cm  
– maximum width: 360 cm  
– diameter: 130 cm  
– core diameter: 76 mm or 150 mm