

Technical data

Basis weight [g/m ²] ISO 536	57
Brightness C/2° [%] ISO 2470	77
Colour D65/10° [%] L*	91
a*	-0.7
b*	2.7
Opacity [%] ISO 2471	94
Gloss Hunter 75° [%] ISO 8245/1	38
Gloss Lehmann 75° [%] ^① ISO 8791-4	34
Roughness PPS 10 [µm] ISO 8791-4	1.0
Bulk [cm ³ /g] ^②	0.96

① The process control is based on Hunter gloss – the Lehmann gloss specification serves as a reference value only

Subject to change. 01/2009

② No guaranteed value – subject to production variations

Please check for availability as all basis weights may be subject to production requirements.

Product description:

MY PLUS *silk gravure* is an improved high-bright SC-A grade for all high quality print production.

Composition:

20 % chemical pulp
80 % mechanical pulp

Examples of use:

Catalogues, magazines, advertising materials

Reel specification:

- Minimum width: 41 cm
- Maximum width: 360 cm
- Diameter: max. 130 cm
- Core diameter: 76 mm or 150 mm