

**Technical data**

Basis weight [g/m <sup>2</sup> ] ISO 536	45	48	51	54	57	60
Brightness D65/10° [%] ISO 2470	70	72	74	74	74	74
Colour D65/10° [%] L*	88	90	91	91	91	91
a*	-1.15	-1.15	-0.75	-0.75	-0.75	-0.75
b*	4.4	4.1	2.5	2.5	2.5	2.5
Opacity [%] ISO 2471	87	89	90	91	92	92
Gloss Hunter 75° [%] <sup>Ⓢ</sup> ISO 8245/1	46	46	52	52	52	52
Gloss Lehmann 75° [%] ISO 8254/1	42	42	53	53	53	53
Roughness PPS 10 [µm] ISO 8791-4	1.00	0.95	0.95	0.90	0.90	0.85
Bulk [cm <sup>3</sup> /g] <sup>Ⓢ</sup>	0.9	0.9	0.8	0.8	0.8	0.8

<sup>Ⓢ</sup> The process control is based on Lehmann gloss – the Hunter gloss specification serves as a reference value only

Subject to change. 10/2008

<sup>Ⓢ</sup> No guaranteed value – subject to production variations

Please check for availability as all basis weights may be subject to production requirements.

**Product description:**

MY CLASSIC *gravure* is a wood containing lightweight coated rotogravure paper.

**Composition:**

Coating weight: 33 % approx.

Base paper composition  
(depending on basis weight):

50–55 % mechanical pulp

35–45 % chemical pulp

5–15 % DIP

**Examples of use:**

45–51 g/m<sup>2</sup> are the catalogue and mailing special grammages

54–60 g/m<sup>2</sup> are the best grammages for top quality magazine print production

**Reel specification:**

– Minimum width: 50 cm

– Maximum width: 450 cm

– Diameter: max. 135 cm

– Core diameter: 76 mm or 150 mm